PRODUCT DATA SHEET

Avery Dennison[®] MPI[™] 1105 Wrapping series

Introduction

Avery Dennison MPI 1105 Wrapping series films are gloss white, premium quality self-adhesive cast vinyls. The films are ultra-conformable and opaque, and offer excellent durability and conformability. Combined with a DOL 1460/1480 Z series overlaminate, Avery Dennison MPI 1105 Wrapping films are highly recommended for applications on rivets and corrugations. In addition, MPI 1105 Wrapping films are available with Easy Apply RS™ technology with the air-egress feature and maximum slideability and repositionability.

Description

Film: 50 micron gloss white cast vinyl

Adhesive: Permanent, acrylic based with grey tie coat and long term removability properties

Backing paper:

MPI 1105 Gloss Two side PE coated StaFlat™ paper, 155g/m2 MPI 1105 EA RS Gloss Two side PE coated StaFlat™ paper, 155g/m2

Conversion

MPI 1105 Wrapping films are ultra-premium products, delivering maximum durability for a wide range of graphics applications. The films are suitable for use on a variety of super-wide format inkjet printers using solvent, eco solvent, UV or latex ink.

To enhance colour and to protect images against UV radiation and abrasion, it is recommended to protect Avery Dennison MPI 1105 Wrapping films using an overlaminate - Avery Dennison DOL 1460 Z Gloss or Avery Dennison DOL 1480 Z Matt conformable overlaminates.

For recommended combinations of DOL films and media, please refer to "Technical Bulletin 5.3". Recommended combinations of Avery Dennison Overlaminates and Avery Dennison Digital Print Media". For information on how to apply Avery Dennison MPI Cast Films, please refer to "Technical Bulletin 5.9. Application methods for Avery Dennison Cast Films".

Uses

- Large fleet graphics on flat, curved, riveted and corrugated surfaces
- Vehicle wrapping applications
- Interior & exterior signs
- Durable advertising, requiring clean removal after intended period of use

Features

- Superb 3D conformability for demanding vehicle and fleet wrapping projects
- Faster, easier installation with Avery Dennison Easy Apply RS technology
- Stunning and consistent image quality on a variety of printers using solvent, eco solvent, UV or latex inks
- Clean long-term removability after years of usage
- Maximum outdoor durability, up to 10 years unprinted



issued: 10/2020

PRODUCT CHARACTERISTICS

Avery Dennison® MPI™ 1105 **Wrapping Series**

Physical properties

Features Caliper, facefilm Caliper, facefilm + adhesive		Test method ¹ ISO 534 ISO 534	Results 50 micron 80 micron
Elongation, reference Dimensional stability Opacity	value	DIN 53455 FINAT FTM 14	200 % 0.4 mm max > 99%
Adhesion MPI 1105	initial ultimate	FINAT FTM-1, stainless steel FINAT FTM-1, stainless steel	300 N/m 650 N/m
MPI 1105 Easy Apply RS	initial ultimate	FINAT FTM-1, stainless steel FINAT FTM-1, stainless steel	280 N/m 420 N/m
Flammability Shelf life Durability, unprinted		Stored at 22° C/50-55 % RH Vertical exposure	Self-extinguishing 2 years 10 years

Temperature range

Features Results Minimum application temperature: ≥ 10 °C - 40 °C to + 80 °C Service temperature:

NOTE: Materials have to be properly dried before further processing, for example laminating, varnishing or application. The residual solvents could change the products' specific features.

For good print and converting result we recommend to let the rolls acclimatize in the print/lamination room at least 24 hours before printing or converting. Too much temperature or humidity deviation between material and room climate can cause layflatness and/or printability issues.

Generally, constant material storage conditions of ideally 20°C (+/-2°C) /50% RH (+/-5%), without too big climate deviations, will support a more robust and stable printing/converting process. For further details, please refer to TB 1.11.

Important

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of these Conditions, the English

version shall be controlling.

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its

All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com

1) Test methods

More information about our test methods can be found on our website.

The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and

