

No. AJFS1709007254FF

Date: SEP.20, 2017

Page 1 of 5

IGEPA NEDERLAND B.V.

BIEZENWEI 16 4004MB TIEL

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description: IGEPA WALLCOVERING TEXTILE AIR B1

**Buyer**: IGEPA

<u>Product Specification:</u> 320gsm <u>Material and Mark</u>: White/Grey

### **Test Requested:**

To determine the flammability (building materials class B1) in accordance with DIN 4102-1 (May 1998) Fire behaviour of building materials and elements Part 1: Classification of building materials, Requirements and testing

Test Results: -- See attached sheet -

Classification: The tested sample meets class B1 building materials requirements of DIN 4102-1 (May

1998).

### **Test Period:**

Sample Receiving Date : SEP.04, 2017

Test Performing Date : SEP.04, 2017 TO SEP.19, 2017

Signed for and on behalf of SGS-CSTC Co., Ltd. Anji Branch

Allen Zou

Technical Manager





No. AJFS1709007254FF

Date: SEP.20, 2017

Page 2 of 5

### I. Test conducted

This test was conducted as per DIN 4102-15:1990 DIN 4102-16:1998 and DIN 4102-1:1998 Clause 6.2, and Classification in according to DIN 4102-1 (May 1998) Clause 6.1-Class B1 materials.

## II. Sample details

General description / Color	IGEPA WALLCOVERING TEXTILE AIR B1					
Density	About 366 g/m²					
Size of sample	1000mm×190mm & 190mm×90mm					

### Conditioning

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of 23  $\pm$  2  $^{\circ}$ C, and a relative humidity of 50  $\pm$  6  $^{\circ}$ C.

#### III. Test results

## 1) "Brandschacht" Test according to DIN 4102-15 &16

Exposed surface: The front face

	Results of "Brandschacht" Test (part 1)							
Line		Unit	Test assemblies No.					
No.			Lengthwise	Widthwise				
1	Specimen fixings according to DIN 4102 part 15, table	/	1	1				
2	Max. flame height above lower sample edge;	cm	40	40				
3	Time 1)	min:s	00:16	00:20				
	Melting/burning through							
4	Time 1)	min:s	00:04	00:05				
	Back of specimen		/	/				
5	Flaming/glowing, Time 1)	min:s	00:05	00:07				
6	Discolouring, Time 1)	min:s	00:03	00:04				
	Burning droplets		/	/				
7	Begin 1)	min:s	00:10	00:12				
	<u>Amount</u>		/	/				
8	Specimen material falling off in separate droplets		$\checkmark$	$\checkmark$				
9	Specimen material falling off continuously		/	/				

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents at <a href="http://www.sgs.com/en/Terms-and-Conditions-Terms-and-Conditions-Terms-and-Conditions-Terms-and-Conditions-Terms-and-Conditions-Terms-and-Noticer of this document is controlled therein. Any holder of this document is Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forey or falsification of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained 50 days only.



No. AJFS1709007254FF

Date: SEP.20, 2017

Page 3 of 5

	Results of "Brandscha	acht" Tes	t (part 2)			
Line		Unit	Test assemblies No.			
No.		Offic	Lengthwise	Widthwise		
	Burning parts		/	/		
10	Begin 1)	min:s	00:11	00:14		
11	Parts of sample falling off separately		/	/		
12	Parts of sample falling off continuously		$\sqrt{}$	$\checkmark$		
13	Duration of continued combustion on mesh base (max.)	min:s	00:27	00:22		
	Burner flame impairment by dripping/falling material		No	No		
14	Time 1)	min:s	/	/		
	Premature ending of test		/	/		
15	End of burning at specimen 1)	min:s	/	/		
16	Time when test terminated (if applicable) 1)	min:s	/	/		
	Burning after end of test		No	No		
17	Duration	min:s	/	/		
18	Number of specimens		/	/		
19	Front of specimen		/	/		
20	Back of specimen		/	/		
21	Height of flame	cm	/	/		
	Glowing after end of test		No	No		
22	Duration	min:s	/	/		
23	Number of specimens		/	/		
24	Front of specimen		/	/		
25	Back of specimen		/	/		
26	Top half of specimen		/	/		
27	Bottom half of specimen		/	/		

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions\_aspy and, for electronic format documents, aspy. Attention; or men and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions\_aspy.attention">http://www.sgs.com/en/Terms-and-Conditions\_aspy.attention</a>; aspy. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

\*\*Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone (86-755) 8307



No. AJFS1709007254FF

Date: SEP.20, 2017

Page 4 of 5

Results of "Brandschacht" Test (part 3)								
Line		Unit -	Test assemblies No.					
No.			Lengthwise		Widthwise			
	Residual length							
28	ingle results	cm	59	61	63	62		
20	origie results	Citi	62	65	67	60		
29	Average of the single results	cm	61.8		63.0			
	Smoke temperature		/		/			
30	Max. of average	$^{\circ}$	145.4		140.7			
31	Time 1)	min:s	07:42		07:48			

Note: 1) time from start of testing

### Class B1 materials:

If the residual length measured after the first test is 45cm or greater, further tests are not required.

## 2) Normal Flammability Test according to DIN 4102-1 Clause 6.2

Bottom edge ignition

Flame application time: 15s

Parameter	Lengthwise					Crosswise				
raiametei		2	3	4	5	6	7	8	9	10
Whether or not flaming extinguished before reach the gauge mark(Yes/No)	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
Whether or not flaming reach the measuring mark within 20 seconds(Yes/No)	No	No	No	No	No	No	No	No	No	No
Time for the flame tip to reach the gauge mark(s)	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA
Afterflame time (s)	0	0	0	0	0	0	0	0	0	0
Max. flame height (cm)	11	13	12	12	11	6	7	9	7	6
Molten dripping(Yes/No)	No	No	No	No	No	No	No	No	No	No
Smoke developments (visual impression)	Medium					Slight				

Note:

NA---Not applicable

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printer overleaf, available on request or accessible at <a href="https://mems.and-conditions.aspx">https://mems.and-conditions.aspx</a> and, for electronic format documents subject to Terms and Conditions for Electronic Documents at <a href="https://mews.ags.com/en/Terms-and-Conditions.Terms-en-Document.aspx">https://mews.ags.com/en/Terms-and-Conditions.Terms-en-Document.aspx</a> Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits or transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduce except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of leaw. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8301

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anj County, Zhejiang Province, China 313300 t t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn 中国 - 浙江 - 安吉县阳光工业四二区阳光大道301号 邮编:313300 t t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

<sup>\*</sup>Reduction in number of test (DIN 4102 Part 16, clause 5.2)



No. AJFS1709007254FF

Date: SEP.20, 2017

Page 5 of 5

#### IV. DIN 4102-1:1998 Criteria for classification

- 1) All materials, except flooring, may be classed as **B1** materials if they meet the following requirements a) and b):
- The test using the 'Brandschacht' apparatus described in DIN 4102-15 (cf. subclause 6.1.3.1) shall be deemed passed if
- The mean value for the residual length (portion of specimen that has not burned or charred; cf. subclause
- 9.1 of DIN 4102-16) of each specimen is at least 15 cm and no individual values are lower than 0 cm,
- The mean effluent temperature does not exceed 200 °C in any test,
- The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.
- b) Pass DIN 4102-1: 1998 sub-clause 6.2.3 Ignitability Test if For each specimen, flaming doesn't reach the gage mark within 20s after flame application.
- Materials may be classed as B2 materials if they pass the ignitibility test specified in DIN 4102-1: 1998 subclause 6.2.5.

For each specimen, flaming doesn't reach the gage mark (150mm marks) within 20s after flame application.

3) Combustible materials which cannot be classed as B1 or B2 materials shall be classed as B3 materials.

### **STATEMENTS**:

This test report does not replace any mandatory certification of the product that may be required.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

### **Photo Appendix:**



SGS authenticate the photo on original report only

\*\*\* End of Report \*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printe overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Tems-and-Conditions.apx.and">http://www.sgs.com/en/Tems-and-Conditions.apx.and</a>, for electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions.frems-en-Document.aspx">http://www.sgs.com/en/Terms-and-Conditions.frems-en-Document.aspx</a> tkenton is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is divised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits or transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduce except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the xull ness otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone: [86-755] 830

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn 中国 - 浙江 - 安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com